



NEO PLASTIC VARNISH

SUEDE

PRODUCT CODE: PV01

TECHNICAL DATA SHEET NO. 05-Lacquers & Varnishes

NOVEMBER 2018

Product Description	A classic polyurethane / alkyd based, interior, scratch, water and alcohol resistant coating for new wood or existing varnished surfaces. NEO Plastic Varnish is a reasonably fast drying wood varnish for interior use. The varnished surface becomes very hard and scratch resistant. Gives a suede finish (also available in high gloss).	
Application Areas	<ul style="list-style-type: none">• Interior use only.• Properly prepared wooden or timber substrates.• NEO Plastic Varnish is suitable for use on wooden furniture, windows, doors, door frames, skirting and panelling.• Due to the good resistance to water and alcohol, bar counters and similar objects can be finished with NEO Plastic Varnish.	
Product Features	<ul style="list-style-type: none">• NEO Plastic Varnish is based on an air-drying resin containing polyurethane.• The varnish is a single pack system and easy to use.• NEO Plastic Varnish dries to a very hard surface, which is resistant to water, alcohol and household detergents.• The varnish coating is hardwearing and very scratch resistant.• The varnish should only be used interior or on exterior objects not exposed to direct sunlight.• Besides application with brush, NEO Plastic Varnish is ideal for use with a spray gun. A much smoother and even surface will be achieved.• Excellent adhesion to properly prepared wooden substrates.• Good water / alcohol mark resistance.• Three coats of NEO Plastic Varnish are used for best results.• Gives a suede finish (also available in high gloss).	
Product Data	Resin Base	Polyurethane resin
	Drying Time	Touch dry: 1-2 hours Hard dry: 3-4 hours
	Solid Matter by Content	By volume: 44% By mass: 51,5%
	Film Thickness	20-25 microns
	Spreading Rate	6-12 square metres per litre. Although the spreading rate will vary with porosity and type of substrate, for uncoated new surfaces work on 6-8 square metres per litre for the first coat and 10-12 square metres per litre for subsequent coats and when applied to sealed substrates.
	Surface Appearance	Silky matt finish
Application Details		
• Mixing	Always stir well before use with a flat paddle.	
• Application Method	Brush or air spray. Paint roller application is not recommended.	
• Thinning	Brush application: apply the first coat diluted 10% with NEO Mineral Turpentine (mt00). Spray application: thin the NEO Plastic Varnish (suede) to 17-19 sec Ford 4 cup with NEO Enamel Thinner (et01).	
• Cleaning	NEO Mineral Turpentine (mt00) or NEO Enamel Thinner (et01).	
• Application	<ul style="list-style-type: none">• Stir well before use.• Sand and remove all dust.• Three coats of NEO Plastic Varnish (suede) are used for best results.• Brush application: apply the first coat diluted 10% with NEO Mineral Turpentine (mt00).• Spray application: thin the NEO Plastic Varnish (suede) to 17-19 sec Ford 4 cup with NEO Enamel Thinner (et01).• Allow to dry 4-6 hours before sanding again.• Remove all dust.	



NEO PLASTIC VARNISH

SUEDE

PRODUCT CODE: PV01

TECHNICAL DATA SHEET NO. 05-Lacquers & Varnishes

NOVEMBER 2018

	<ul style="list-style-type: none">• With brush or spray, apply two more generous coats leaving 4-6 hours between coats.• Only apply in ventilated areas, keep away from all ignition sources, flames and sparks.• Do not eat, drink or smoke while applying.• Do not apply before 09:00 and after 16:00 in the winter.• Although the spreading rate will vary with porosity and type of substrate, for uncoated new surfaces work on 6-8 square metres per litre for the first coat and 10-12 square metres per litre for subsequent coats and when applied to sealed substrates.• For interior use only.• Clean up application equipment with NEO Mineral Turpentine (mt00) or NEO Enamel Thinner (et01).
Surface Preparation	
<ul style="list-style-type: none">• New Wood	<ul style="list-style-type: none">• Sand wood well to a smooth surface.• Make sure wood is clean and free of dust.• Apply one coat of NEO Plastic Varnish (suede) diluted with approximately 10% NEO Mineral Turpentine (mt00).• When dry, sand well again to a smooth surface.• Apply another two coats of NEO Plastic Varnish (suede) undiluted.
<ul style="list-style-type: none">• Existing Varnished Surfaces	<ul style="list-style-type: none">• Sand the wooden substrate well.• Remove all dust.• If the previously varnished area is firm and solid (no sign of flaking, peeling, cracking, etc.), sand down well until the surface is completely matt.• Apply two coats of NEO Plastic Varnish (suede) undiluted.• But if the varnish shows signs of cracking etc., remove old varnish completely back to bare wood.• Apply a thick layer of NEO Paint Remover (pr00) on the varnished surface. After about 15-20 minutes lift off the paint remover together with the varnish using a scraper.• Rinse well with warm soap water to remove all traces of the paint remover.• When dry, sand well and apply one coat of NEO Plastic Varnish (suede) diluted with approximately 10% NEO Mineral Turpentine (mt00).• When dry, sand well again to a smooth surface.• Apply another two coats of NEO Plastic Varnish (suede) undiluted.• Never apply paint remover on veneer.
Colour Range and Quantities	<ul style="list-style-type: none">• NEO Plastic Varnish (suede) is available in clear only.• Available in 1 litre and 5 litres.
Precautions	<ul style="list-style-type: none">• NEO Plastic Varnish (suede) is highly flammable.• Use only in well ventilated areas and do not eat, drink or smoke during application.• The product contains no toxic substances.
Disclaimer	NEO Paints can not be held liable if the product fails due to improper surface preparation or application.
NEO PAINTS FACTORY (PTY) LTD Reg No 2002/214	
12 Bell Street, Southern Industrial Area PO Box 5005 Windhoek, NAMIBIA Tel. +(264) 61-384 700 – Fax +(264) 61-233 914	Hanna Mupatani Road PO Box 762 Walvis Bay, NAMIBIA Tel. +(264) 64-204 026 – Fax +(264) 64-204 010